

TDS Code: D8189008



青岛伦敦杜蕾斯有限公司
QINGDAO LONDON DUREX CO., LTD.

地址: 青岛高新技术产业开发区岙东路上马段 1-13 号
Address: No. 1-13 Shangma Part, Ao-dong Road High-tech Industrial Development Zone, Qingdao, China
邮编 Post Code: 266114 电话 Tel: (0086) 0532 66966193 传真 Fax: (0086) 0532 87838708

产品合格证明 Certificate of Conformance

合格证编号 No. of Certificate COC629224

兹证明该批产品符合 GB/T 7544 / ISO 4074 标准<<天然橡胶胶乳男用避孕套技术要求与试验方法>>
This certificate certifies that this batch of product conforms with the standard GB/T 7544 / ISO 4074
Natural Rubber Latex Male Condoms – Requirements and Test Methods.

产品名称 Description of Product: 天然胶乳橡胶避孕套 Natural Latex Rubber Condom

产品商标 Trade Mark: 杜蕾斯® Durex® 或 or 杜蕾斯™ Durex™

品名 Brand: 超薄装 Fetherlite Feel

产品批号 Lot No.: 1002762895

产品识别码 ID No.: N/A

生产日期 Manufacture Date: 2024-11

失效日期 Expiry Date: 2029-10

产品代码 FG Code: 3106132

包装数量 Pack Size: 12's

内包产品代码 Foiled Condom Code: 50019346

报告人 Reported By: 任信 日期 Date: 2024/11/12

批准人 Approved By: 任信芳 日期 Date: 2024/11/12

参阅号 Ref: QSF 8.2-5.0201 签发 Issue: 12 页数 Page: 1 of 1 日期 Date: 10/2022



CS 扫描全能王
3亿人都在用的扫描App



青岛伦敦杜蕾斯有限公司 QINGDAO LONDON DUREX CO., LTD.

题目Subject: 分析证明 Certificate Of Analysis

地址: 青岛高新技术产业开发区香东路上马段1-13号

Address No.1-13 Shangma Part, Aodong Road High-tech Industrial Development Zone, Qingdao,

邮编Post Code: 266114 电话Tel: (0086) 0532 66966193 传真Fax: (0086) 0532 87838708

品名 Brand: 超薄装Fetherlite Feel

产品类型 Type: 52mm

批号 Lot No.: 1002762895

包装规格 Pack Size: 12's

颜色 Color: 无色透明Transparent

润滑液类型 Lubricant Type: 硅油Silicone oil, TAK Transatak

生产日期 MFG. Date:

失效日期 EXP. Date:

2024-11

2029-10

内包数量 Quantity Foiled (只 PCS): 383904

包装数量 Quantity Packed (托 CAR): 2666

样品收到日期 Sample Arrival Date: 05/12/2024

检测时间 Tested Date: 05/12/2024

检验标准Tested According To: GB/T 7544 / ISO 4074

技术要求 Requirements	抽样量 (只) Sample Size (PCS)	AQL	限值 Limits	不合格水平 Reject Level	检验结果Test Results			
					范围 Range	平均值 Average	不合格数量 NO. Failed	合格/不合格 Passed / Failed
尺寸 Dimmension:								
长度Length (毫米mm)	13	N/A	160 Minimum.	1	182-186	184	0	合格Passed
宽度Width (毫米mm)	13		标称 STD ± 2	1	52.0-53.0	52.5	0	合格Passed
厚度Thickness(毫米mm)	13		***根据不同规格 Individual Spec	1	0.047-0.050	0.048	0	合格Passed
爆破试验 Burst Test:								
老化前Initial 体积(Volume (升l))	200 []	1.5	**19.0 Minimum. []	8 []	22.0-42.0	33.5	0	合格Passed
	315 [v]		22.0 Minimum. [v]	11 [v]				
	500 []		*25.0 Minimum.[]	15 []				
其它Other ____			****					
压强Pressure (千帕 kPa)			1.0 Minimum.		1.10-1.70	1.50		
针孔 Freedom From Holes								
	315 [v]	0.25		3 [v]	-	-	0	合格Passed
	500 []			4 []	-	-		
其它Other ____					-	-		
可见缺陷 Visible Defect								
	315 [v]	0.40		4 [v]	-	-	0	合格Passed
	500 []			6 []	-	-		
其它Other ____					-	-		
独立包装可见开口 Individual Containers With Visibly Open Seals								
	315 [v]	0.40		4 [v]	-	-	0	合格Passed
	500 []			6 []	-	-		
其它Other ____					-	-		
包装密封性 Package Integrity								
	32 [v]	0.65		1 [v]	-	-	0	合格Passed
其它Other ____					-	-		
包装和标识检验 Packaging & Labelling Checks	13	N/A	无缺陷 No Failure				0	合格Passed

* 仅限于 Only for EO75 & AP EO80

** 仅限于 Only for SWCF45

*** CON1/46&CON2/3/4/17&CON69&CON33/66&CON28&CON34&CON9&CON10&CON35/36/37&CON26&CON13&CON14&CON11&CON24&CON27 产品厚度按照公司办法进行并仅作参考, 其他产品厚度按照ISO4074测量。CON1/46&CON2/3/4/17&CON69&CON33/66&CON28&CON34&CON9&CON10&CON35/36/37&CON26&CON13&CON14&CON11&CON24&CON27 will be measured as per company spec and only for information. Others will be measured as ISO4074.

**** 仅限于特殊要求。 Only for special requirements.

结论Decision: ☒ 合格Accepted ☐ 不合格Failed

报告人Prepared(实验室技术员Lab Technician): 于计华 日期Date: 2024/12/09

批准人Approved By(质控经理QC. MGR.): 任磊 日期Date: 2024/12/09

参阅号Ref: QSF: 825-020 签发 Issue: QO14 页数Page: 1 of 1



CS 扫描全能王

3亿人都在用的扫描App